

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)


(51) International Patent Classification ⁶ : G01V 15/00		A1	(11) International Publication Number: WO 97/04338
			(43) International Publication Date: 6 February 1997 (06.02.97)
(21) International Application Number: PCT/GB96/00367			(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT, UA, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).
(22) International Filing Date: 16 February 1996 (16.02.96)			
(30) Priority Data: 9514581.9 17 July 1995 (17.07.95) GB 9521442.5 19 October 1995 (19.10.95) GB			
(71) Applicant (for all designated States except US): SCIENTIFIC GENERICS LIMITED [GB/GB]; Harston Mill, Harston, Cambridge CB2 5NH (GB).			
(72) Inventors; and (75) Inventors/Applicants (for US only): DAMES, Andrew, Nicholas [GB/GB]; 74 De Freville Avenue, Cambridge CB4 1HU (GB). CROSSFIELD, Michael, David [GB/GB]; Perme Drift, Burton End, West Wickham, Cambridge CB1 6SD (GB).			
(74) Agents: ABRAMS, Michael, John et al.; Haseltine Lake & Co., Hazlitt House, 28 Southampton Buildings, Chancery Lane, London WC2A 1AT (GB).			

Published
With international search report.

(54) Title: IMPROVEMENTS RELATING TO MAGNETIC TAGS OF MARKERS

(57) Abstract

A magnetic tag or marker is described which is capable of functioning as a multi-bit information carrying tag. The tag may be attached to an article and then used as a means of identifying that article, generally as it enters or is positioned within an interrogation zone. The tag comprises (a) a first magnetic material characterised by high permeability, low coercivity and a non-linear B-H characteristic; and (b) a second magnetic material which is capable of being permanently magnetised, the second magnetic material being magnetised with a non-uniform field pattern (A, B, C). Detection systems for use with such tags, and write/read system using them, are also disclosed.



Tag with 3 bias regions and 1 bias level

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

IMPROVEMENTS RELATING TO MAGNETIC TAGS OR MARKERS

This invention relates to magnetic tags or markers, to systems for storing data in such tags and for subsequently retrieving the data remotely, and to
5 methods utilising such tags and systems.

Such tags and systems have a wide variety of applications. These include inventory control, ticketing, automated shopping systems, monitoring work-in-progress, security tagging and access control,
10 anti-counterfeiting and item verification.

Prior Art

There are a number of passive data tag systems
15 currently available. The most widely-used is based on optically-read printed patterns of lines, popularly known as barcodes. The tag element of such systems is very low-cost, being typically just ink and paper. The readers are also relatively low cost, typically
20 employing scanning laser beams. For many major applications the only real drawback to barcodes is the need for line-of-sight between the reader and the tag.

For applications where line-of-sight is not
25 possible, systems not employing optical transmission have been developed. The most popular employ magnetic induction for coupling between the tag and the interrogator electronics. These typically operate with alternating magnetic fields in the frequency range of
30 50kHz to 1MHz, and generally employ integrated electronic circuits ("chips") to handle receive and transmit functions, and to provide data storage and manipulation. In order to avoid the need for a battery, power for the chip is obtained by
35 rectification of the interrogating signal received by an antenna coil. In order to increase the power transferred, and to provide discrimination against unwanted signals and interference, the coil is usually

-2-

resonated with a capacitor at the frequency of the interrogation signal carrier frequency. A typical product of this type is the TIRIS system manufactured by Texas Instruments Ltd.

5

Other multi-bit data tag systems have employed conventional h.f. radio technology, or technologies based on surface acoustic waves or magnetostriction phenomena.

10

The Invention

The present invention relates to a new type of passive data tag system which employs small amounts of very high-permeability magnetic material, and an alternating magnetic field for interrogation. Since the magnetic material can be in the form of a thin foil, wire or film, it can be bonded directly to paper or plastic to form self-supporting tags.

20 More particularly, according to one aspect of the present invention there is provided a magnetic marker or tag, which comprises (a) a first magnetic material characterised by high permeability, low coercivity and a non-linear B-H characteristic; and (b) a second
25 magnetic material which is capable of being permanently magnetised, characterised in that said second magnetic material is magnetised with a non-uniform field pattern.

Appropriate manufacturing techniques for the new
30 label are well-known in conventional label manufacture, and in particular in the manufacture of 1-bit labels for retail security applications. Alternatively, the magnetic elements could be incorporated directed into the items to be tagged during manufacture.

35 In such a tag, the field pattern in the second material may vary in amplitude and/or direction and/or

-3-

polarity. The second magnetic material is advantageously formed of discrete, magnetised sections of a magnetic bias material, e.g. a plastics material substrate coated with a ferromagnetic layer or film, e.g. of ferrite. The desired magnetic field pattern may be written onto a strip or tape of magnetic bias material. Thus it is possible to use audio or video recording tape as the bias material.

The magnetic field pattern may vary across the width of said strip or tape as well as along its length.

Preferably, the first magnetic material has an extrinsic relative permeability greater than 10^3 and a coercivity not more than 10 A/m. In one embodiment, the first magnetic material takes the form of an elongate strip or wire; in another, it is in the form of a thin film. When a strip form of first magnetic material is used, it preferably has dimensions in the ranges: width - from 0.1mm to 10mm, more preferably from 0.5mm to 5mm; and thickness from $5\mu\text{m}$ to $500\mu\text{m}$, more preferably from $10\mu\text{m}$ to $100\mu\text{m}$. When in thin film form, the first magnetic material is advantageously in the form of one or more patches each having an area in the range 1mm^2 to 500mm^2 , preferably from 10mm^2 to 100mm^2 . Such patches may each have a thickness in the range from $0.1\mu\text{m}$ to $10\mu\text{m}$.

If desired, the said first and second magnetic layers may be supported by a substrate formed of paper or a plastics material. Such a support, however, may not be required. The tag will generally be adapted to be secured to an article to serve as an identifying tag for that article. It may, for example, be used as an antipilferage or anti-counterfeiting tag. It may alternatively be used as a verification tag. In this context, it may for example be used to confirm that an article has been assigned to its proper position during

-4-

a sorting or distribution process.

According to another aspect, the present invention provides a data storage and retrieval system which comprises a plurality of magnetic markers or tags as claimed in claim 1 and a detection system comprising
5 (i) first means for generating an alternating magnetic field; (ii) second means for detecting harmonics generated by the interaction between the first magnetic material of the tag and the alternating magnetic field
10 produced in use by said first means; and (iii) third means for correlating the detection of harmonics by said second means with the alternating magnetic field generated by said first means.

In such a data storage and retrieval system, the
15 third means is preferably arranged to determine the amplitude and phase of the harmonics generated by the interaction of the first magnetic material of the tag and the alternating magnetic field, the harmonics of interest normally being selected from harmonics in the
20 range of 2nd to 100th. The third means may be arranged to determine the characteristics of the harmonics produced by the marker and to compare the detected characteristics with information in a data bank, this information serving to correlate the detected
25 characteristics with known characteristics relating to items on an inventory.

In one embodiment, the third means is arranged to determine the number of harmonic bursts detected per cycle of the generated alternating magnetic field.
30 Alternatively, the third means may be arranged to determine the point or points within each cycle of the alternating magnetic field at which harmonic bursts are detected.

In preferred embodiments, the detection system is
35 arranged to determine the characteristics of harmonic bursts produced by the tag or marker and to compare the

-5-

detected characteristics with information in a data bank, this information serving to correlate the detected characteristics with known characteristics relating to items on an inventory. The characteristics
5 selected for analysis may include the shape of the envelope of said harmonic bursts.

The means for generating an alternating magnetic field is advantageously arranged so that, in use, it generates a first, high frequency alternating magnetic
10 field and a second, low frequency alternating magnetic field. For example, the high frequency alternating magnetic field may be at a frequency in the range of from 250Hz to 20kHz, advantageously in the range from 3kHz to 10kHz; and the low frequency alternating
15 magnetic field may be at a frequency in the range of from 1Hz to 250Hz, advantageously in the range of from 5Hz to 50Hz.

Currently preferred interrogation systems are adapted to generate a high frequency alternating
20 magnetic field at a frequency in the range of from 1kHz to 10kHz, e.g. from 4kHz to 8kHz, and a low frequency alternating magnetic field at a frequency in the range of from 8Hz to 50Hz, e.g. from 10Hz to 20Hz.

The system will typically operate with a high
25 frequency alternating magnetic field in the range 1kHz - 10kHz, together with a low frequency field typically in the range 1 - 100Hz.

Alternatively a single alternating field may be used. Such a field may have a frequency in the range
30 of from 50Hz to 20kHz. This arrangement, however, requires more complex data processing, as will be described hereinafter.

Embodiments of the invention provide a multi-bit data tag system which employs low-frequency inductive
35 magnetic interrogation, and avoids the need for complex, expensive tags.

-6-

The tag consists of a high permeability, low coercivity magnetic alloy element combined with a medium coercivity ferromagnetic element capable of being permanently magnetised. As explained above, the first or high permeability magnetic element preferably has an extrinsic relative permeability $>10^3$ and preferably at least 10^4 ; and a coercivity <10 Amps/m. This generally requires a material with high intrinsic permeability and low coercivity, in a form such as a long thin strip or a thin film which avoids major internal demagnetisation effects. Strip materials are readily-available commercially from suppliers such as Vacuumschmelze (Germany), Allied-Signal Corp (USA) and Unitika (Japan). Thin film material is currently manufactured in high volume by IST (Belgium) for use in retail security labels.

The second magnetic material, which functions as a magnetic bias material, preferably has medium coercivity material and its nature is less critical; it may, for example, be steel, nickel, ferrite etc. A ferrite-based material such as is commonly used for manufacturing audio and video recording tape is particularly convenient for use with thin film high permeability material, since it can be deposited directly onto the back of the plastic layer supporting the film. This makes for very simple, low-cost manufacture.

The tag as thus described is broadly similar in construction and materials to certain types of label used in retail security applications, and supplied by companies such as Sensormatic (USA), Knogo (USA), 3M (USA) and Esselte Meto (Germany). In such types of labels the medium coercivity layer is magnetised when the product is sold, rendering the label inactive either by biasing it into saturation, or by magnetically cutting the label into short

-7-

low-permeability sections.

In the present invention the second magnetic material or biasing element is magnetised with a field pattern which varies spatially in amplitude and/or sign and/or direction. This can be done by using discrete magnetised sections of bias-layer material, or by writing the bias pattern on a continuous layer using for example a magnetic recording head. The label is preferably interrogated by a low-frequency alternating magnetic field with a simultaneously-present low amplitude high-frequency alternating magnetic field. The low frequency field has sufficient amplitude to overcome the local biasing created by the magnetised layer of the label. Clearly, if the bias levels are different in different regions, then the bias will be overcome at different points (times) in the low frequency field scan.

The high-frequency interrogation field has lower amplitude by a factor of typically 3 than the low frequency field. When the local bias has been overcome by the low frequency field, harmonics of the high frequency will be produced by the non-linear B-H characteristic of the high permeability material. These can readily be detected by a suitably-tuned receiver. By noting the pattern of harmonic bursts during the low frequency cycle, the particular magnetisation pattern of the label can be detected.

Retail security systems already exist which use interrogation schemes which are appropriate for the coded labels described. For example, Esselte Meto sells products using low frequency scanning at 16 Hz, high frequency interrogation at 6.25 kHz, and 2nd harmonic detection. In other products high frequencies of 5kHz and 7.5 kHz are used with a 16 Hz scan, detection of the intermodulation product at 12.5 kHz being used. In both cases the coded tags of this

-8-

invention may be detected, and this requires only software changes to decode the data content of the tag.

If the levels of magnetisation used in the label are represented by +1, 0 and -1, then signal bursts can
5 be produced at three points in the low frequency cycle. In principle this will allow for at least 3 unique label "signatures" (3 bursts/cycle, 2 bursts/cycle and 1 burst/cycle). If time of burst occurrence can also be employed, further codes can be distinguished.

10 However burst time is dependant on the amplitude of the low frequency interrogating field, and is therefore dependant on label orientation. -For this reason timing information is harder to exploit reliably.

With more levels of magnetisation, many more codes
15 (i.e. magnetic signatures) can be provided, the ultimate limits coming from the size of label required, and the resolution of the detection system. As already mentioned, account also needs to be taken of the effect of orientations, since, as the label is rotated in the
20 interrogation field, the anisotropic nature of the label means that the effective field amplitude seen by the label will change, and the positions of the signal bursts will move.

It is easiest to relate to coding schemes where
25 the presence or absence of distinct independent features correspond to data bits. However, this is not essential. A great variety of complex arbitrary signal shapes can be created by suitably configuring the field pattern stored on the label. These shapes are highly
30 repeatable in manufacture, and can readily be recognised by pattern-matching software in the signal receiver. This type of coding extends the number of codes which can be produced with a small number of bias levels, and is particularly suitable for applications
35 where highly distinctive codes are required, e.g. in anti-counterfeiting.

-9-

The size of tag will depend on sensitivity of the detection system and more fundamentally on the smallest length of strip or area of thin film material which can provide adequately high permeability (allowing for
5 shape demagnetisation). For the narrowest, thinnest strip material currently freely available (approximately 1mm wide x 20 μ m thick) this is around 20mm. A tag as described above, providing 3 unique unambiguous patterns, would therefore need to be around
10 60mm long.

Thin film material with an active layer around 1 μ m thick can readily maintain high permeability for patches of about 5mm x 5mm; and so using this material the 3-code label example could be implemented in a
15 label 15mm x 5mm.

Detailed Description

For a better understanding of the invention, and
20 to show how the same may be carried into effect, reference will now be made, by way of example, to the accompanying drawings, in which:

FIGURE 1a illustrates diagrammatically a magnetic tag in accordance with a first embodiment of this
25 invention;

FIGURE 1b illustrates diagrammatically a magnetic tag in accordance with a second embodiment of this invention;

FIGURE 2 illustrates diagrammatically the
30 application of two bits of data to a magnetic tag in accordance with the invention;

FIGURES 3 and 4 illustrate one mode of detecting the presence of, and reading data from, a magnetic tag in accordance with the invention;

35 FIGURE 5 illustrates diagrammatically the magnetic response of five simple tags in accordance with this

-10-

invention each of which comprises three zones or bias regions;

FIGURE 6 illustrates diagrammatically the magnetic response of eleven further simple tags in accordance with this invention each of which comprises two zones or bias regions and which carry a magnetic pattern with two possible levels of magnetisation;

FIGURE 7 illustrates diagrammatically a first tag interrogation or read system suitable for use with tags of this invention; and

FIGURE 8 illustrates diagrammatically a second tag interrogation or read system suitable for use with tags of this invention.

Referring now to the drawings, Fig. 1a shows one form of tag in accordance with this invention. The tag comprises a first magnetic material 1 in the form of an elongate strip of a material characterised by high permeability, low coercivity and a non-linear B-H characteristic. Suitable materials for this purpose include amorphous magnetic alloy materials such as those available from Vacuumschmelze under the designation 6025 or 6066. The magnetic material does not need to be amorphous, however; a suitable alternative may readily be selected from the Permalloy materials. Because of its magnetic behaviour, this material can be termed a soft magnetic strip.

Magnetic strip 1 is secured, for example by means of a contact adhesive (not shown), to a second magnetic material 2 in the form of a rectangular lamella of a material which is capable of being permanently magnetised; the material preferably has high remanence and a medium coercivity. For ease of illustration, the two magnetic materials 1 and 2 are depicted slightly apart.

A variety of materials may be used to form lamella 2; examples include foils formed of steels, nickel or

-11-

nickel alloys; and tapes comprising a substrate carrying a magnetic layer or film, e.g. of ferrite. Such tapes are available commercially for audio or video recording purposes. In this embodiment, a
5 ferrite-loaded polymer tape is used. The tape was approximately 10 μ m thick and had a coercivity of 300 oersteds and was obtained from Kurz Foils (UK) Ltd. as part B920224D (this is generally used in cards such as credit cards, swipe cards and the like where the
10 material constitutes the magnetic stripe).

When the tag is ready for use, lamella 2 carries data in the form of a magnetic pattern which may be relatively simple or relatively complex. For ease of illustration and to assist in explaining the mode of
15 operation of the invention, only simple magnetic patterns are illustrated in the drawings. It will be appreciated, however, that complex magnetic patterns may be applied to the lamella 2 by, for example, writing using a magnetic recording head or a series of
20 such heads. By such simple means, complex magnetic patterns can be generated and stored on the tag. With suitable protocols, this magnetic pattern is used to represent data - in particular (but not exclusively) data which serves to identify an article to which the
25 tag is attached.

In use, the lamella 2 influences the magnetic behaviour of the soft magnetic material 1; it is thus convenient to refer to the medium coercivity material as a bias material, and lamella 2 as a bias element.

30 Figure 1b shows an alternative form of tag in which the first (soft) magnetic material is in the form of a thin film 3 of magnetic material of the type produced by IST (Belgium) for use in retail security labels. This is secured, for example by means of a
35 contact adhesive (not shown), to bias element 2'. For ease of illustration, the two magnetic materials are

-12-

depicted slightly apart. Lamella 2' is formed of the same material as lamella 2 in Fig. 1a, but here it is in the form of a square 5mm x 5mm.

Figure 2 illustrates the manner in which data is carried by a tag in accordance with this invention. The bias element 2 is magnetised in a first region A and unmagnetised in a second region B. The direction of magnetisation in region A is indicated by the poles N-S.

Figures 3 and 4 show a convenient mode of interrogating a tag such as those of Figure 1. Fig. 3 shows a plot of applied magnetic-field H against time; the applied field comprises two components, the first being a high frequency, low amplitude field (not shown separately but evident from the form of field H); and the second being a low frequency, high amplitude field - represented in Figure 3 by the triangular waveform L. This type of field is advantageous because it permits relatively simple techniques to be used in the detection system; an alternative approach would be to use just on alternating magnetic field of relatively large amplitude and a more sophisticated detection set up utilising data processing and pattern recognition techniques known *per se*.

When a tag of this invention - e.g. that of Fig. 1a - is positioned within an interrogation zone to which the alternating field H of Fig. 3 is applied, the soft magnetic strip 1 interacts with the applied field and generates a detectable response which is indicative of the magnetic character of the whole tag. The behaviour of such materials in magnetic fields is well known *per se*. The soft magnetic material generates a magnetic response in which harmonics of the applied field signal are present, the detailed magnetic character of the response representing a magnetic signature for the tag. With exceedingly simple tags

-13-

such as that of Fig. 2 (which is a two-bit tag by virtue of having two magnetically distinct regions A and B) a suitable detector (examples of which will be given hereinafter) will produce an output of the form shown in Fig. 4. For reasons of clarity, the scale of the time axes in Figs. 3 and 4 is not the same. The form of the response is shown as a plot of detected signal S against time. Dashed line T, linking Figs. 3 and 4, shows the instantaneous field in Fig. 3 at which signal S of Fig. 4 intersects the time axis - i.e. the instantaneous output signal strength is zero at the moment when the instantaneous applied field is zero.

Figures 3 and 4 help to illustrate the mode of operation of the tag. When the instantaneous field strength is zero, that part of the soft magnetic material in strip 1 above region B of bias element 2 is able to respond as it would in the free condition, since region B carries no magnetisation; it thus generates a harmonic burst illustrated in Fig. 4 by the sine wave on the right of plot S. The other portion of strip 1, i.e. that over region A of bias element 2, generates a similar response but at a different time - namely the time at which the applied field H counteracts the field imposed on the strip 1 by region A. Consequently region A of element 2 gives rise to a signal indicated as the sine wave to the left of signal S in Fig. 4 - in this case before the signal from portion B is obtained.

Figure 5 illustrates a tag with three zones, A, B and C, and illustrates the detected signals S'₁ - S'₃, for a variety of magnetic configurations of these three zones. The plots of detected signals S' given in Fig. 5 are analogous to that of Fig. 4.

The first plot S'₁ represents a control in which all three zones A - C are unmagnetised. Here, the overlying soft magnetic strip 1 suffers no magnetic

-14-

bias from element 2 and behaves effectively as though it were free of lamella 2; and the signal S'_1 sweeps out a relatively large area. In plot S'_2 , two thirds of the bias element (i.e. zones A and B) have zero magnetisation, which leads to a sine wave response ss_{a+b} which sweeps out an area two thirds of that of signal S'_1 . The magnetised zone C gives rise to sine wave signal component ss_c which sweeps out an area one third of that of signal S'_1 . Signal plot S'_3 is a mirror image of that of S'_2 ; this is due to the fact that the polarity of zone C is reversed in plot S'_3 .

Similar considerations lead to the observed structure of the detected signal in the cases of plots S'_4 and S'_5 ; it will be observed that these two plots, representing magnetisation conditions of $+1/0/-1$ and $-1/0/+1$ respectively - are redundant.

Figure 6 illustrates the responses obtained with just two regions, A and B, in the bias element 2, but with two bias levels, i.e. a total of five magnetisation states ($+2 \dots 0 \dots -2$). The resultant signal mapping will be understood by analogy to the description of Figs. 3, 4 and 5 above.

In the examples illustrated above, the magnetisation within any given zone is taken to be uniform; and consequently the observed patterns of detected signal are geometrically simple, being sine waves which sweep out areas proportional (at a first approximation) to the length of the strip material generating the response or, correspondingly, to the areas of zones such as A, B, C in lamella 2 which acts upon that length of soft magnetic material. It is not, however, a requirement that such a simple magnetic field pattern be employed; on the contrary, in many cases it will be advantageous to use a magnetic field pattern which varies in orthogonal directions across the lamella 2, thereby constituting the basis of a

-15-

magnetic signature for the tag. When using tags with more complex field patterns, it is necessary to use more sophisticated detection systems; these, however, can utilise known data processing and pattern
5 recognition techniques to identify the signature obtained when any given tag is interrogated by an appropriate magnetic field.

Referring now to Figure 7, a presently preferred form of detection system is shown. This comprises two
10 alternating current sources 71 and 72, operating at frequencies f_1 and nf_2 , respectively, which are combined by way of summing amplifier 74, the frequency of current source 72 first being divided by n by frequency
15 divider 73. The output of summing amplifier 74 is amplified by amplifier 75, and is passed through a low pass filter 76 with a cut-off frequency f_2 to a transmitter coil 77. The harmonic responses to the interrogation signal of any tags or markers of this
20 invention present in the interrogation zone are received by a receiver coil 77', which may be the same coil as transmitter coil 77. Band pass filter 78 removes any signals received which fall outside a predetermined bandwidth, e.g. $nf_2 \pm m.f_1$, and then passes the residual signal through low noise amplifier
25 79 to phase detector 80, which correlates the phase of the signal with that of current source 72. The signal is then passed through low pass filter 81 with a cut-off frequency $m.f_1$ to analogue-to-digital converter 83, and thence to digital signal processor 84, which
30 analyses the signal for harmonic responses at the $m.f_1$ sidebands caused by the presence of a tag in the interrogation zone. This information is available as a time domain signal of a particular shape which repeats at the low frequency f_1 . The resultant data output is
35 at 85. Processor 84 contains pattern recognition circuitry known *per se*; if the shape of the time

-16-

domain signal corresponds within acceptable bounds to a shape which is known to be the "magnetic signature" of a predetermined tag, then a correspondence condition is achieved and, by using a data bank or look-up table, the identity of the article to which the tag is attached can be given.

Figure 8 shows an alternative interrogation system in which a single current source at alternating frequency f_1 is supplied to a low noise amplifier 92, and is passed through a low pass filter 93 to a transmitter coil 94. The harmonic responses to the interrogation signal of any tags or markers of this invention present in the interrogation zone are received by a receiver coil 94', which may be the same coil as transmitter coil 94. Broad band filter 95 removes unwanted frequency ranges from the signal from 94' and the output passes to low noise amplifier 96 and thence to multichannel or comb filter 97 ($nf_1 - mf_1$) which permits harmonic numbers $n - m$ to be analysed. The output of filter 97 passes to detector 98 and thence to analogue-to-digital converter 99. The output from converter 99 is processed by digital processor 100 which operates in a manner analogous to processor 84 described above in relation to Figure 7 to generate an output 101.

-17-

CLAIMS:

1. A magnetic marker or tag, which comprises (a) a first magnetic material characterised by high permeability, low coercivity and a non-linear B-H characteristic; and (b) a second magnetic material which is capable of being permanently magnetised, characterised in that said second magnetic material is magnetised with a non-uniform field pattern.
2. A magnetic marker or tag as claimed in claim 1, characterised in that the field pattern in said second material varies in amplitude.
3. A magnetic marker or tag as claimed in claim 1, characterised in that the field pattern in said second material varies in polarity and/or direction.
4. A magnetic marker or tag as claimed in claim 1, 2 or 3, characterised in that said second magnetic material is formed of discrete, magnetised sections of a magnetic bias material.
5. A magnetic marker or tag as claimed in claim 1, 2 or 3, characterised in that said second magnetic material is formed by writing a magnetic field pattern onto a strip or tape of magnetic bias material.
6. A magnetic marker or tag as claimed in claim 5, characterised in that said magnetic field pattern varies across the width of said strip or tape.
7. A magnetic marker or tag as claimed in any preceding claim, characterised in that said first magnetic material has an extrinsic relative permeability greater than 10^3 and a coercivity not more

-18-

than 10 A/m.

8. A magnetic marker or tag as claimed in claim 7,
characterised in that said first magnetic material is
5 in the form of an elongate strip or wire.
9. A magnetic marker or tag as claimed in claim 7,
characterised in that said first magnetic material is
in the form of a thin film.
- 10
10. A magnetic marker or tag as claimed in claim 8,
characterised in that said strip-has dimensions in the
ranges: width - from 0.1mm to 10mm; and thickness from
5 μ m to 500 μ m.
- 15
11. A magnetic marker or tag as claimed in claim 10,
characterised in that said strip has dimensions in the
ranges: width - from 0.5mm to 5mm; and thickness from
10 μ m to 100 μ m.
- 20
12. A magnetic marker or tag as claimed in claim 9,
characterised in that said thin film material is in the
form of one or more patches each having an area in the
range 1mm² to 500mm².
- 25
13. A magnetic marker or tag as claimed in claim 12,
characterised in that said one or more patches each
have an area in the range from 10mm² to 100mm².
- 30
14. A magnetic marker or tag as claimed in claim 12,
13 or 14, characterised in that said one or more
patches each have a thickness in the range from 0.1 μ m
to 10 μ m.
- 35
15. A magnetic marker or tag as claimed in any
preceding claim, characterised in that said first and

-19-

second magnetic layers are supported by a substrate formed of paper or a plastics material.

16. A magnetic marker or tag as claimed in any
5 preceding claim, characterised in that the marker is adapted to be secured to an article to serve as an identifying tag for that article.
17. A magnetic marker or tag as claimed in any claim
10 16, characterised in that the marker or tag serves as an antipilferage or anti-counterfeiting tag.
18. A magnetic marker or tag as claimed in any claim
15 16, characterised in that the marker or tag serves as a verification tag.
19. A data storage and retrieval system which comprises a plurality of magnetic markers or tags as claimed in claim 1 and a detection system comprising
20 (i) first means for generating an alternating magnetic field; (ii) second means for detecting harmonics generated by the interaction between the first magnetic material of the tag and the alternating magnetic field produced in use by said first means; and (iii) third
25 means for correlating the detection of harmonics by said second means with the alternating magnetic field generated by said first means.
20. A data storage and retrieval system as claimed in
30 claim 19, characterised in that said third means is arranged to determine the amplitude and phase of the harmonics generated by the interaction of the first magnetic material of the tag and the alternating magnetic field, the harmonics of interest being
35 selected from harmonics in the range of 2 to 100.

-20-

21. A data storage and retrieval system as claimed in claim 19, characterised in that said third means is arranged to determine the characteristics of said harmonics produced by the marker and to compare the detected characteristics with information in a data bank, said information serving to correlate the detected characteristics with known characteristics relating to items on an inventory.
22. A data storage and retrieval system as claimed in claim 19, 20 or 21, characterised in that said first means is arranged so that, in use, it generates a first, high frequency alternating magnetic field and a second, low frequency alternating magnetic field.
23. A system as claimed in claim 19, 20, 21 or 22, characterised in that said third means is arranged to determine the number of harmonic bursts detected by said second means per cycle of the alternating field generated by said first means.
24. A system as claimed in claim 19, 20, 21, 22 or 23, characterised in that said third means is arranged to determine the point or points within each cycle of said alternating field at which harmonic bursts are detected by said second means.
25. A system as claimed in any one of claims 19 to 24, characterised in that said detection system is arranged to determine the characteristics of harmonic bursts produced by the marker and to compare the detected characteristics with information in a data bank, said information serving to correlate the detected characteristics with known characteristics relating to items on an inventory.

-21-

26. A system as claimed in claim 25, characterised in that said detection system is arranged to measure the shape of the envelope of said harmonic bursts.
- 5 27. A system as claimed in any one of claims 19 to 26, characterised in that said first means is adapted to generate an alternating magnetic field at a frequency in the range of from 50Hz to 20kHz.
- 10 28. A system as claimed in claim 22, characterised in that said first means is adapted to generate a high frequency alternating magnetic field at a frequency in the range of from 250Hz to 20kHz..
- 15 29. A system as claimed in claim 28, characterised in that said first means is adapted to generate an alternating magnetic field at a frequency in the range of from 3kHz to 10kHz.
- 20 30. A system as claimed in claim 22 or 28, characterised in that first means is adapted to generate a low frequency alternating magnetic field at a frequency in the range of from 1Hz to 250Hz.
- 25 31. A system as claimed in claim 30, characterised in that said first means is adapted to generate a low frequency alternating magnetic field at a frequency in the range of from 5Hz to 50Hz.
- 30 32. A system as claimed in claim 31, characterised in that said first means is adapted to generate a high frequency alternating magnetic field at a frequency in the range of from 1kHz to 10kHz and a low frequency alternating magnetic field at a frequency in the range
- 35 of from 8Hz to 50Hz.

-22-

33. A system as claimed in claim 32, characterised in that said first means is adapted to generate a high frequency alternating magnetic field at a frequency in the range of from 4kHz to 8kHz and a low frequency
5 alternating magnetic field at a frequency in the range of from 10Hz to 20Hz.

34. A method of coding articles so as to make it possible to distinguish between different classes of
10 articles and/or to distinguish between individual articles within a given class, which comprises (1) applying to said articles a magnetic marker or tag comprising (a) a first magnetic material characterised by high permeability, low coercivity and a non-linear
15 B-H characteristic; and (b) a second magnetic material which is capable of being permanently magnetised; and (2) generating a predetermined, non-uniform permanent magnetic field pattern in said second magnetic material by magnetising said second magnetic material either
20 before or after it has been applied to said article, said magnetic field pattern being selected so as to be readable with suitably configured apparatus and to be distinctive of said article or of the class to which said article belongs when so read.

25
35. A method of detecting the presence of an article within a predetermined interrogation zone, which comprises (A) attaching to or incorporating into the article, before the article reaches said interrogation
30 zone, a magnetic marker as claimed in claim 12 and which carries a unique magnetic code so as to be distinctive of the article; (B) determining the magnetic interaction between said magnetic marker and an applied magnetic field capable of interacting with
35 said magnetic marker to generate a detectable response; (C) recording in a directory the correlation between

-23-

said article, said magnetic marker and its magnetic interaction determined by step B; and (D) subjecting the volume defined by said interrogation zone to substantially the same magnetic conditions as were used
5 in step B while one or more unknown articles are located within said zone, and determining the resultant magnetic interaction(s); (E) comparing the detected interaction(s) with data in said directory; and (F) generating a response indicating the nature of the
10 article whenever correlation data in said directory provides a match between the magnetic interaction generated in step (D) and that in step (B).

36. A method according to claim 35, characterised in
15 that said applied magnetic field comprises (i) a first alternating, low frequency magnetic field and (ii) a second alternating, high frequency magnetic field.

1/6

Figure 1a: Basic Strip Tag Construction




Figure 1b: Basic Thin Film Tag Construction





Figure 2: Tag biased to provide 2 signal features



SUBSTITUTE SHEET (RULE 26)

2/6

Figure 3: Possible tag interrogation field
Low frequency scanning field combined
with high frequency field




Figure 4: Detected signal from tag

SUBSTITUTE SHEET (RULE 26)

3/6





Figure 5: Tag with 3 bias regions and 1 bias level

SUBSTITUTE SHEET (RULE 26)

4/6





Figure 6: Tag with 2 bias regions and 2 bias levels

SUBSTITUTE SHEET (RULE 26)


5/6



Typical Interrogation System (1)

FIGURE 7.

SUBSTITUTE SHEET (RULE 26)



harmonic numbers $n - m$ analysed

Typical Interrogation System (2)

FIGURE 8.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 96/00367

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 G01V15/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 G01V G06K G08B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	FR,A,2 358 713 (MINNESOTA MINING & MFG) 10 February 1978 see claims 1,2,7-11	1,2,15, 16,19
Y	WO,A,93 14474 (RSO CORP N V) 22 July 1993 see abstract; claims 1-3,8; figures 1,2 see page 6, line 32 - page 8, line 17	1,2,15, 16,19
Y	US,A,4 075 618 (MONTEAN SAMUEL) 21 February 1978 see abstract; figure 8	16
A	EP,A,0 096 182 (ALLIED CORP) 21 December 1983	
A	WO,A,92 12402 (SCIENT GENERICS LTD) 23 July 1992	
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "&" document member of the same patent family

Date of the actual completion of the international search

20 May 1996

Date of mailing of the international search report

12.06.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

de Heering, P

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 96/00367

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>US,A,4 274 089 (GILES TERENCE G) 16 June 1981</p> <p>-----</p>	

Form PCT/ISA/210 (continuation of second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT

Information on patent family members

Inter. Application No
PCT/GB 96/00367

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR-A-2358713	10-02-78	US-A- 4075618	21-02-78
		AU-B- 515029	12-03-81
		AU-B- 2701977	18-01-79
		CA-A- 1089050	04-11-80
		DE-A- 2732167	26-01-78
		GB-A- 1581844	31-12-80
		JP-C- 1324191	27-06-86
		JP-A- 53010300	30-01-78
		JP-B- 60051758	15-11-85
		NL-A- 7707727	17-01-78
WO-A-9314474	22-07-93	SE-B- 469673	16-08-93
		AU-B- 3413593	03-08-93
		AU-B- 3413693	03-08-93
		AU-B- 3651893	03-08-93
		CA-A- 2128431	22-07-93
		CA-A- 2128432	22-07-93
		CA-A- 2128433	22-07-93
		EP-A- 0623237	09-11-94
		EP-A- 0627106	07-12-94
		EP-A- 0624241	17-11-94
		EP-A- 0626666	30-11-94
		JP-T- 7503085	30-03-95
		JP-T- 7503066	30-03-95
		JP-T- 7503344	06-04-95
		SE-A- 9200145	21-07-93
		SE-A- 9203258	21-07-93
		SE-A- 9203479	21-07-93
		WO-A- 9314478	22-07-93
		WO-A- 9314370	22-07-93
US-A-4075618	21-02-78	AU-B- 515029	12-03-81
		AU-B- 2701977	18-01-79
		CA-A- 1089050	04-11-80
		DE-A- 2732167	26-01-78
		FR-A,B 2358713	10-02-78
		GB-A- 1581844	31-12-80
		JP-C- 1324191	27-06-86
		JP-A- 53010300	30-01-78
		JP-B- 60051758	15-11-85

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 96/00367

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-4075618		NL-A- 7707727	17-01-78
EP-A-0096182	21-12-83	US-A- 4510490	09-04-85
		AU-B- 560069	26-03-87
		AU-B- 1294983	08-12-83
		CA-A- 1200872	18-02-86
		JP-C- 1412501	27-11-87
		JP-A- 58219677	21-12-83
		JP-B- 62014873	04-04-87
WO-A-9212402	23-07-92	AU-B- 1155692	17-08-92
		AU-B- 1156692	17-08-92
		CN-A- 1063951	26-08-92
		EP-A- 0565583	20-10-93
		EP-A- 0565584	20-10-93
		WO-A- 9212401	23-07-92
		JP-T- 6507476	25-08-94
		JP-T- 7503061	30-03-95
		NZ-A- 241215	26-07-95
		US-A- 5420569	30-05-95
US-A-4274089	16-06-81	GB-A- 1599120	30-09-81
		DE-A- 2920263	29-11-79
		FR-A,B 2426361	14-12-79
		JP-C- 1438134	19-05-88
		JP-A- 55004588	14-01-80
		JP-B- 62045504	28-09-87
		NL-A- 7903841	21-11-79

THIS PAGE BLANK (USPTO)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)